Freudenberg Sealing Technologies

Material 80 NBR 186349

auburn cross linking: sulfur

revision index 3	revis i 8/27/2	i on date 2008			ра	ge 1/2
Physical properties				required	actual	
Density DIN EN ISO 1183-1					1.30	g/cm³
Hardness DIN ISO 7619-1					81	Shore
Modulus 100 %, DIN 53504, S2					7.6	MPa
Tensile strength DIN 53504, S2					13.3	MPa
Elongation at break DIN 53504, S2					206	%
Certificates RoHS	Country I	Part	Remark		Expires	unlimited ✓

Freudenberg Sealing Technologies

Material 80 NBR 186349

auburn cross linking: sulfur

revision index 3 revision date 8/27/2008

page 2/2

No ASTM D2000 properties available

Temperature range: -30 °C to 100 °C (static -40 °C)

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.