

Material

98 AU 928

revision index	revision date	page	1 / 2
4	2/22/2012		
Physical properties	required	actual	
Density DIN EN ISO 1183-1, 23 °C	1.19 ±0.02	1.19	g/cm³
Hardness DIN ISO 7619-1, Shore A, 23 °C	97 +2/-3	97	Shore
Hardness DIN ISO 7619-1, Shore D, 23 °C	55 ±3	55	Shore
Modulus 50 %, DIN 53504, S2, 23 °C	> 14	18	MPa
Modulus 300 %, DIN 53504, S2, 23 °C	> 29	36	MPa
Tensile strength DIN 53504, S2, 23 °C	> 48	57	MPa
Elongation at Break DIN 53504, S2, 23 °C	> 300	400	%
Tear strength DIN 53515, A, 23 °C	> 110	140	KN/m
Compression set DIN ISO 815, B, 24 h, 100 °C, 20 %	---	33	%
Compression set DIN ISO 815, B, 70 h, 100 °C, 10 %	---	40	%
Compression set DIN ISO 815, B, 24 h, 125 °C, 10 %	---	55	%
Low Temperature DIN 53765, DSC	---	-37	°C
Torsions pendulum test DIN EN ISO 6721-2A	---	-17	°C

Material 98 AU 928

revision index

4

revision date

2/22/2012

page 2 / 2

No ASTM D2000 properties available

Temperature-range: - 35 °C to + 110 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.