

# Material

## 95 AU V 149

revision index

4

revision date

12/20/2010

page

1 / 2

### Physical properties

	required	actual	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	1.20 ±0.02	1.20	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1, Shore A, 23 °C	95 +2/-3	95	Shore
<b>Hardness</b> DIN ISO 7619-1, Shore D, 23 °C	45 +4/-3	45	Shore
<b>Tensile strength</b> DIN 53504, S2, 23 °C	> 30	46	MPa
<b>Elongation at Break</b> DIN 53504, S2, 23 °C	> 380	510	%
<b>Tear strength</b> DIN 53515, A, 23 °C	---	100	KN/m
<b>Compression set</b> DIN ISO 815, B, 24 h, 100 °C, 20 %	---	41	%
<b>Low Temperature</b> DIN 53765, DSC	---	-37	°C
<b>Torsions pendulum test</b> DIN EN ISO 6721-2A	---	-22	°C

# Material 95 AU V 149

**revision index**

4

**revision date**

12/20/2010

**page** 2 / 2

## No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.