

Material F 52803

white

revision index	revision date	page	
1	10/19/2009	1 / 2	
Physical properties		required	actual
Density DIN EN ISO 1183-1, 23 °C		2.18 +0.02/-0.04	2.17 g/cm ³
Hardness DIN ISO 7619-1, Shore D, 23 °C		56 ±2	55 Shore
Tensile strength DIN 53455, S2, 23 °C		27 +8/-7	24.3 MPa
Elongation at Break DIN 53455, S2, 23 °C		300 ±100	311 %

Material F 52803

white

revision index

revision date

1

10/19/2009

page 2 / 2

No ASTM D2000 properties available

Temperature-range: - 200 °C to 260 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.